
BUTYLEN-AS40 Plus/-R20 HT



Product information



Special advantages

- Real co-extruded 3-ply tape as the inner layer and two-ply tape as the outer layer.
- Excellent mechanical protection and excellent corrosion prevention combined with an outstanding tape elasticity.
- DIN-DVGW approved system: **C 50** (EN 12068, DIN 30672).
- Compatible with factory coatings made of PE, PP, FBE, PU, CTE and bitumen.
- For temperatures up to +85°C (+185°F)

Two-tape system for the corrosion prevention coating of metal pipes and pipelines in accordance with DIN 30672 and EN 12068.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trendsetting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Description

BUTYLEN-AS40 Plus/-R20 HT is a

cold applied two-tape system for the corrosion prevention of metal pipes and pipelines in extreme corrosion conditions and mechanical stresses. Compared to the single tape system **BUTYLEN-AS40 Plus**, a robust and UV resistant surface of the encasement is achieved with the outside tape **BUTYLEN-R20 HT**.

The BUTYLEN-AS40 Plus/-R20 HT

system is covered by a DIN-DVGW certificate (Reg.-No.: DV-5180BT0429).

Standard designation: EN 12068 – C 50

DIN 30672 - C 50



BUTYLEN-AS40 Plus/-R20 HT pro-

vides a self-amalgamation of the tapes in the overlapping area, which means that a tight and durable hosetype encasement is established. **BUTYLEN-AS40 Plus/-R20 HT** is basically impermeable for water vapor and oxygen and it is resistant against soil bacteria and electrolytes.

BUTYLEN-AS40 Plus/-R20 HT is compatible with factory coatings made of PE, PP, FBE, PU, CTE and Bitumen.

The system **BUTYLEN-AS40 Plus/** -R20 HT consists of: **BUTYLEN-HT Primer**

A solvent containing primer in accordance with EN 12068 and DIN 30672 for the corrosion prevention with **BUTYLEN** tapes.

BUTYLEN-AS40 Plus

A real co-extruded 3-ply plastic tape made from stabilized polyethylene carrier with butyl rubber adhesive on both sides.

BUTYLEN-R20 HT

A real co-extruded two-ply plastic tape made from stabilized polyethylene carrier film with a butyl rubber adhesive on one side.

The outstanding connection between the adhesive and the carrier film is guaranteed by the co-extruded intermediate layer. The adhesive layer grows completely together with the outside layer of **BUTYLEN-AS40 Plus**.



BUTYLEN-R20 HT

Universal Corrosion Coatings Pty. Ltd. 16 Sperry Drive, Tullamarine, VIC 3043, Australia T: +61 3 9310 3515 | F: +61 3 9310 3524 | www.unicc.com.au

BUTYLEN-AS40 Plus

Typical product properties

Property		Unit	BUTYLEN-AS40 Plus Typical value	BUTYLEN-R20 HT Typical value	Test method	
Carrier film color		-	black, yellow or blue	white, black or blue	-	
Butyl adhesive color inside		-	grey	black	-	
Butyl adhesive color outside		-	Black	-	-	
Tape thickness		mm	≥0.8	≥0.5		
Carrier film thickness app.		mm	≥0.2	≥0.3	ISO 4591	
Inside adhesive layer thickness app.		mm	≥0.5	≥0.2	ASTM D1000	
Outside adhesive layer thickness		mm	≥0.1	-		
Elongation at break		%	≥600	≥500	DIN 30672	
Tape strength	+23°C (+73,4°F)	N / cm	≥100	≥65	EN 12068	
Dielectric strength		kV / mm	≥35	≥35	DIN 53481	
Water absorption	+23°C (+73,4°F) 1 day / 30 days	%	≤0.1 / ≤0.4	≤ 0.1 / ≤0.4	DIN 53495 ASTM D570	
Water vapor permeability		g /m² 24h	≤ 2 * 10 ⁻¹	≤ 5 * 10 ⁻²	DIN 53122	

BUTYLEN-AS40 Plus/-R20 HT with BUTYLEN-HT Primer

Unit	BUTYLEN-AS40 Plus/R20 HT Typical value		Required value		Test method	
Ohm m ²	≥10 ¹⁰		≥10 ⁸		EN 12068	
Ohm cm	n ≥10 ¹⁵		Not stated		DIN 53482 ASTM D257	
N / cm	+23°C (+73.4°F)	+50°C (+122°F)	+23°C(+73.4°F)	+50°C(+122°F)		
	≥25	≥3	≥10	≥1	EN 12068	
	≥45	≥5	Not s	tated	ASTM D1000	
N / cm	+23°C (+73.4°F) +50°C (+122°F)					
	≥30	≥4	≥10	≥2	EN 120C0	
	≥30	≥3	≥2	≥2	EN 12068	
	≥3	≥3	≥2	≥2		
	+50°C (+122°F)					
mm	≥1.1 0.4 / 10		≥0.6		EN 12068	
J	≥16		≥15		EN 12068	
mm	<6		<20		EN 12068	
N / cm ²	+23°C (+73.4°F)					
	≥15		≥ 5		EN 12068	
	≥15		≥ 5		1	
	Ohm m ² Ohm cm N / cm N / cm mm	Unit Typica Ohm m² ≥1 Ohm cm ≥1 Ohm cm ≥1 N / cm ≥25 ≥45 ≥45 ×30 ≥30 >30 ≥30 ≥30 ≥30 1 0.4 J ≥1 Mm ≥1 N / cm 230	Typical value Ohm m² $\geq 10^{10}$ Ohm cm $\geq 10^{10}$ Ohm cm $\geq 10^{15}$ N / cm ≥ 25 ≥ 3 ≥ 45 ≥ 5 ≥ 30 ≥ 45 N / cm ≥ 30 ≥ 4 ≥ 30 ≥ 3 N / cm ≥ 30 ≥ 4 ≥ 30 ≥ 3 ≥ 3 Mm ≥ 30 ≥ 3 Mm ≥ 1.1 $0.4 / 10$ J ≥ 1.6 $0.4 / 10$ Mm ≤ 1.6 1.6 Mm < 6 $+23°C (+73.4°F)$	Unit Typical value Require Ohm m ² $\geq 10^{10}$ ≥ 1 Ohm cm $\geq 10^{15}$ Not s P ≥ 25 ≥ 3 $\geq 10^{10}$ N / cm ≥ 25 ≥ 3 $\geq 10^{10}$ N / cm $\pm 23^{\circ}$ C (+73.4°F) $\pm 50^{\circ}$ C (+122°F) $\pm 23^{\circ}$ C (+73.4°F) N / cm ± 30 ≥ 4 $\geq 10^{\circ}$ N / cm ± 30 ≥ 4 $\geq 10^{\circ}$ Mm ± 30 ≥ 3 $\geq 2^{\circ}$ Mm ≥ 1.1 $= 2^{\circ}$ $0.4 / 10$ $= 2^{\circ}$ $= 2^{\circ}$ J $\geq 16^{\circ}$ $= 2^{\circ}$ Mm $\leq 16^{\circ}$ $= 2^{\circ}$ N / cm ² $\geq 216^{\circ}$ $= 2^{\circ}$	UnitTypical valueRequired valueOhm m2 $\geq 10^{10}$ $\geq 10^{8}$ Ohm cm $\geq 10^{15}$ Not statedN / cm ≥ 25 ≥ 3 ≥ 10 ≥ 25 ≥ 3 ≥ 10 ≥ 1 ≥ 45 ≥ 5 Not stated $\times 10^{10}$ ≥ 25 ≥ 3 ≥ 10 ≥ 25 ≥ 3 ≥ 10 ≥ 1 ≥ 45 ≥ 5 Not stated $\times 10^{10}$ ≥ 2 ≥ 3 $\geq 10^{10}$ $\times 10^{10}$ ≥ 30 ≥ 4 $\geq 10^{10}$ ≥ 2 ≥ 30 ≥ 3 ≥ 2 ≥ 2 ≈ 30 ≥ 3 ≥ 2 ≥ 2 ≥ 30 ≥ 3 ≥ 2 ≥ 2 ≥ 30 ≥ 3 ≥ 2 ≥ 2 ≥ 30 ≥ 3 ≥ 2 ≥ 2 $\Rightarrow 10$ $= 1.1$ $= 0.6$ $0.4 / 10$ ≤ 1.5 ≤ 1.5 mm < 6 < 20 N / cm^2 ≥ 1.5 ≤ 1.5 N / cm^2 ≥ 1.5 ≥ 1.5	

BUTYLEN tapes can be easily applied manually. The processing with the original **DEKOMAT**[®] wrapping devices is even more efficient. For **BUTYLEN** tapes with widths of > 50 mm, we recommend the use of the **DEKOMAT**[®] wrapping device to guarantee an excellent processing quality.

Ordering information and packaging

				Content per box				
	Width [mm]	Tape length [m]	Tape area per roll (m²)	Number of rolls	Total tape area (m²)	Total tape length (m)	App. weight (kg)	
Core Ø 41 mm	30	15	0.45	16	8	270	7.0	
	50	15	0.75	12	9	180	9.0	
	100	15	1.5	6	9	90	10.2	
Core Ø 78 mm	100	70	7	3	21	210	19.0	
	150	70	10.5	2	21	140	19.0	
Core Ø 41 mm	50	30	1.5	12	18	360	11.0	
	100	30	3.0	6	18	180	11.0	
	100	70	7	3	21	210	13.0	
Core Ø 78 mm	150	70	10.5	2	21	140	13.0	
	Core Ø 78 mm	$ \begin{bmatrix} [mm] \\ 30 \\ 50 \\ 100 \\ 00 \\ 00 \\ $	$ \begin{bmatrix} [mm] & [m] \\ 30 & 15 \\ 50 & 15 \\ 50 & 15 \\ 100 & 15 \\ 100 & 15 \\ 100 & 70 \\ 150 & 70 \\ 150 & 70 \\ 150 & 70 \\ 150 & 30 \\ 100 & 30 \\ 100 & 30 \\ 100 & 70 \end{bmatrix} $	[mm] [m] per roll (m²) Core Ø 41 mm 30 15 0.45 50 15 0.75 100 15 1.5 Core Ø 78 mm 100 70 7 Core Ø 78 mm 50 30 1.5 Core Ø 41 mm 50 30 1.5 Core Ø 78 mm 100 70 7	Imm] Im] per roll (m²) Number of rolls Core Ø 41 mm 30 15 0.45 16 50 15 0.75 12 100 15 1.5 6 Core Ø 78 mm 100 70 7 3 Core Ø 41 mm 50 30 1.5 12 Core Ø 41 mm 50 30 1.5 12 Core Ø 41 mm 100 30 3.0 6 Core Ø 78 mm 100 70 7 3	Width [mm] Tape length [m] Tape area per roll (m²) Number of rolls Total tape area (m²) Core Ø 41 mm 30 15 0.45 16 8 Core Ø 41 mm 50 15 0.75 12 9 100 15 1.5 6 9 Core Ø 78 mm 100 70 7 3 21 Core Ø 41 mm 50 30 1.5 12 18 Core Ø 41 mm 50 30 3.0 6 18 Core Ø 78 mm 100 70 7 3 21	Width [mm] Tape length [m] Tape area per roll (m²) Number of rolls Total tape (m²) Total tape length (m) Core Ø 41 mm 30 15 0.45 16 8 270 Core Ø 41 mm 50 15 0.75 12 9 180 Core Ø 78 mm 100 70 7 3 21 210 Core Ø 41 mm 50 30 1.5 12 18 360 Core Ø 41 mm 50 30 1.5 12 18 360 Core Ø 41 mm 50 30 3.0 6 18 180 Core Ø 78 mm 100 70 7 3 21 210	

Additional lengths and widths are available on request.