

Petrolatum Mastic HT

An integral component of the UCC Petrolatum System, providing long term corrosion protection for steel substrates in a multitude of environments.

| | |
|--------------------|--|
| Description | UCC Petrolatum Mastic HT is a neutral petrolatum compound stabilised with inert fillers, complemented with corrosion inhibitors and reinforced with synthetic fibres. |
| Uses | UCC Petrolatum Mastic HT is used for sealing, filling, and profiling applications where a protective waterproof and non-setting mastic is required. It can be used to contour pipes and profile irregular surfaces prior to the application of UCC Petrolatum Tapes. |
| Features | <ul style="list-style-type: none"> - Surface tolerance on marginally prepared substrates; St 2.0 - Conforms to irregular shapes and profiles - Can be applied to cold, wet substrates - Unaffected by water, acid, salts, or bacterial attack - Excellent sealing properties - Nil VOC's - Ease of application at high and low temperature extremes - Ready for immediate service, no curing time - Conforms with AWWA C 217-04 |
| Application | <ul style="list-style-type: none"> - Prepare surface to St 2 std. - Apply UCC Petrolatum Primer to substrate at a spread rate of 3 kg/m² approx. - Profile projections and voids with UCC Petrolatum Mastic. - Spirally apply tape incorporating 55% overlap to achieve a double thickness with circumferential turn. - Overwrap tape with UCC PVC OverWrap, spirally applied with 55% overlap. |

| Properties | Value |
|----------------------------|---------------|
| Flash Point | 182°C |
| Specific Gravity | 1.09 Avg |
| Drop Melting Point | 90°C |
| Application Temperature | -10°C to 55°C |
| Service Temperature | -20°C to 75°C |
| Excursion Peak Temperature | 80°C |

| Product Packaging | | | |
|-------------------|----------------|-----------------|--------------------|
| Unit Size (Kg) | Unit Packaging | Blocks / Carton | Carton Weight (kg) |
| 3 | Block | 8 | 25 |

Universal Corrosion Coatings Pty. Ltd.

16 Sperry Drive, Tullamarine, Victoria 3043, Australia

Phone: +61 3 9310 3515

Fax: +61 3 9310 3524

Website: www.unicc.com.au

The above information is given in good faith based on data and knowledge considered to be true and accurate and is offered for the user's assistance.